

Coating material curable thermally and with actinic radiation, and its use

Patent claims

5

Sub A3 1. A coating material curable thermally and with actinic radiation, comprising

10

(a1) at least one constituent containing

(a11) at least two functional groups which serve for crosslinking with actinic radiation, and

15

(a12) at least one functional group which is able to undergo thermal crosslinking reactions with the hydroxyl and/or thiol groups (a21) in the constituent (a2),

20

and

(a2) at least one branched, cyclic and/or acyclic C<sub>9</sub>-C<sub>16</sub> alkane functionalized with at least two hydroxyl or thiol groups or with at least one hydroxyl and at least one thiol group (a21).

25

2. The coating material as claimed in claim 1, characterized in that it additionally comprises one or more of the components

30

(a3) at least one photoinitiator,

(a4) at least one thermal crosslinking initiator,

35

(a5) at least one reactive diluent curable thermally and/or with actinic radiation,

(a6) at least one coatings additive,

5 (a8) at least one organic solvent.

4. The coating material as claimed in one of claims 1 to 3, characterized in that said constituent (a1) comprises a urethane (meth)acrylate and/or polyester (meth)acrylate.

6. The coating material as claimed in any of claims 1 to 5, characterized in that the functionalized alkane (a2) has a boiling point of over 200°C.

8. The coating material as claimed in any of claims 1 to 7, characterized in that the functionalized alkane (a2) contains primary and/or secondary, especially primary and secondary, hydroxyl and/or thiol groups.

9. The coating material as claimed in any of claims 1 to 8, characterized in that the functionalized alkane (a2) is a polyol (a2).

[illegible]

Sub A3  
cont.

10. The coating material as claimed in claim 9, characterized in that the polyols (a2) are diols and/or triols (a2).
- 5 11. The coating material as claimed in claim 10, characterized in that the polyols (a2) are positionally isomeric dialkyloctanediols, especially diethyloctanediols.
- 10 12. The coating material as claimed in claim 11, characterized in that the polyol (a2) consists of or comprises 2,4-diethyl-1,5-octanediol.
- 15 13. The use of the coating material as claimed in any of claims 1 to 12 in automotive OEM finishing, automotive refinish, the coating of plastics, the coating of furniture, and industrial coating, including coil coatings and container coatings, for the production of clearcoats and of multicoat color and/or effect coating systems.
- 20 14. The use of the coating material as claimed in any of claims 1 to 12 for producing a clearcoat or a multicoat color and/or effect coating system, where at least one clearcoat film of a coating material as claimed in any of claims 1 to 12 curable thermally and with actinic radiation is applied to the surface of the primed or unprimed substrate or wet-on-wet to the surface of a basecoat film and is cured together, where appropriate, with the basecoat film.
- 25 30

Add A4